

Product Description / characteristics

Appearance: Silo (heated), Delivered weight/plates 23T

Properties	Test method	AMTECK® RWM-Series		
		RO	RONT	ROR
Kinematic Viscosity mm ² /s at 100 °C, in the rang	ASTM D445	28.00-34.00	19.00-25.00	45.00-80.00
Kinematic Viscosity mm ² /s at 40 °C, in the rang		Not normalized	260.0-310.0	3830
Refractive index at 20°C, in the range	ASTM D1747	1.4900-1.5050	1.4900-1.5050	1.5200-1.5450
Flash point (COC) °C	ASTM D92	275	240	290
Aniline point °C	ASTM D611		118	103.8
Viscosity gravity constant (VGC)	ASTM D2140		0.81	0.84
Pour point °C	ASTM D97	-9	-14	-45
TAN mg KON/g	ISO 6619			0.05
Sulfur content wt% max.	ASTM D6481	0.8	0.6	2
Density at 15 °C kg/m ³	ASTM D 4052	902.1	984.5	938
Density at 20 °C kg/m ³		905.3	891.4	935
PCA content wt%	IP 346	3	3	2.9
Saturated/aromatic/polar compounds wt%	IP 469	54/42/4	57/40/3	26/67/7
Carbon type distribution: Ca/Cn/Cp wt%	ASTM D2140		6/26/68	19/20/61
Color (CNT Color Scale) max.	ASTM D1500	6	6	6
Appearance	visual	Bright and clear without foreign additives		

Legal Statement

The information in this technical description is for reference purposes only. It can be considered as the basis for determining whether material is acceptable for specific applications. Because it is not possible to anticipate all applications of materials and operating conditions, AMT makes no warranty and assumes no liability for the use of the information specified in the catalog. This information may be changed without notice.