

Product Description

Appearance: granulated, packed in Bigbags

Application: window profile

Properties

Feature	Unit	Standard	Value
Hardness, 15 sec	Shore A	ISO 868	60
Density	g/cm ³	ISO 1183	0.99
Tension at 100% elongation	MPa	ISO 37	1.5
Tensile stress	MPa	ISO 37	9.0
Elongation at break, (100 mm/min)	%	ISO 37	860
Compression set 22h at 23°C	%	ISO R 815 B	19
Compression set 22h at 70°C, relaxation at 23°C	%	ISO R 815 B	38
Compression set 22h at 85°C, relaxation at 23°C	%	ISO R 815 B	45
Melt flow rate (230°C; 5 kg)	g/10 min	ISO 1133	6.0

Legal Statement

The information in this technical description is for reference purposes only. It can be considered as the basis for determining whether material is acceptable for specific applications. Because it is not possible to anticipate all applications of materials and operating conditions, AMT makes no warranty and assumes no liability for the use of the information specified in the catalog. This information may be changed without notice.